

Chevron Grease	NLGI Grade	Thickener	Base Oil	Base Oil KV @40C, mm2/s, cSt	Dropping Point (F)	Min Operating Temp (F)	Max Operating Temp (F)	PDS
Black Pearl Grease EP	1, 2	Polyurea	Mineral	145	518	-40	350	<a href="#">Link</a>
Chevron Open Gear Grease		Inorganic Clay	Mineral	6532				<a href="#">Link</a>
Coupling Grease	1	Lithium	Mineral	885	374	-20	325	<a href="#">Link</a>
Delo Extreme Grease EP	1	Polyurea	Mineral	22	473	-58	302	<a href="#">Link</a>
Delo Grease EP	00, 0	Lithium Complex	Mineral	226	455	-40	270	<a href="#">Link</a>
Delo Grease ESI EP (Delo Grease ESI)	2	Lithium Complex	Mineral	261	511	-25	350	<a href="#">Link</a>
Delo Grease ESI HD EP	1, 2	Lithium Complex	Mineral	383	509	-15	350	<a href="#">Link</a>
Delo Grease ESI HD Moly 3% EP	1, 2	Lithium Complex	Mineral	383	509	0	325	<a href="#">Link</a>
Delo Grease ESI HD Moly 5% EP	1, 2	Lithium Complex	Mineral	383	509	-15	350	<a href="#">Link</a>
Delo Starplex EP	1, 2	Lithium Complex	Mineral	226	471	-40	350	<a href="#">Link</a>
Delo Syn-Grease SFE EP	00, 0	Polyurea	Synthetic	130	446	-50	375	<a href="#">Link</a>
Delo Syn-Grease SXD 220	1	Lithium Complex	Synthetic	200	509	-40	450	<a href="#">Link</a>
Multifak EP	000, 00, 0, 1, 2	Lithium	Mineral	349, 112, 173, 173, 173	320, 320 340, 367, 370	-31, -31, -22, -4, 5	158, 170, 210, 257, 260	<a href="#">Link</a>
Sil-X Grease	1	Silica	Mineral	467	500	15	400	<a href="#">Link</a>
SRI Grease	2	Polyurea	Mineral	116	470	-22	350	<a href="#">Link</a>
Texclad	2	Calcium	Mineral	1000	210	0	175	<a href="#">Link</a>
Ulti-Plex HV Synthetic Grease EP	1.5	Lithium Complex	Synthetic	1248	536	-40	450	<a href="#">Link</a>
Ulti-Plex Synthetic Grease EP	1.5	Lithium Complex	Synthetic	302	536	-60	450	<a href="#">Link</a>
Ultra-Duty Grease EP	0, 1, 2	Lithium	Mineral	400	342, 342, 374	-15	270, 280, 290	<a href="#">Link</a>